



S O L D E R S

SOLDERING TIN

The soldering tin is produced under strict surveillance of quality from cleanest alloys according to DIN 1707. We offer a large variety of lead free alloys to our customers:

* Sn96,5/Ag3,5	SP - 221°C
* Sn95,5/Ag3,8/Cu0,7	SB - 217°C – 219°C
* Sn99,3/Cu0,7	SP - 227°C
* Sn95,5/Ag4/Cu0,5	SP - 217°C

Of course we still offer the standard alloys like:

<input type="checkbox"/> Sn60/Pb40	SB - 183°C - 190°C
<input type="checkbox"/> Sn63/Pb37	SP - 183°C
<input type="checkbox"/> Sn62/Pb36/Ag2	SP - 179°C

but all other alloys which are known in electronics can be ordered.

Delivery form :

- 250 g bars
- 1000 g bars
- Blocks with loop 3,5 kg

Solder Chemistry ; Fragnerstraße 4 ; D-84034 Landshut
Tel. ++49/871/4309500 ; Fax. ++49/871/43095020
e-Mail: info@SolderChemistry.com ; www.SolderChemistry.com

The engineering data shown here has been compiled by the producer using commonly accepted procedures. Although the data is considered accurate, we cannot guarantee its accuracy, the results obtained from its use, or any patent infringement resulting from its use. The data is supplied on the condition that the user shall conduct tests to determine material suitability for a particular application.